## Lag Screws

**Bolts & Cap Screws** 





Hex Lag Screws													
Basic Product Diameter		Threads Per Inch	E Body or Shoulder Diameter		F Width Across Flats			G	)		H		S
								Width Across Corners		Head Height		Shoulder Length	
			Мах	Min	Basic	Max	Min	Max	Min	Basic	Max	Min	<sup>c</sup> Min
No. 10	0.1900	11	0.199	0.178	9/32	0.281	0.271	0.323	0.309	1/8	0.140	0.110	0.094
1/4	0.2500	10	0.260	0.237	7/16	0.438	0.425	0.505	0.484	11/64	0.188	0.150	0.094
5/16	0.3125	9	0.324	0.298	1/2	0.500	0.484	0.577	0.552	7/32	0.235	0.195	0.125
3/8	0.3750	7	0.388	0.360	9/16	0.562	0.544	0.650	0.620	1/4	0.268	0.226	0.125
7/16	0.4375	7	0.452	0.421	5/8	0.625	0.603	0.722	0.687	19/64	0.316	0.272	0.156
1/2	0.5000		0.515	0.482	3/4	0.750	0.725	0.866	0.826	11/32	0.364	0.302	0.156
5/8	0.6250	5	0.642	0.605	15/16	0.938	0.906	1.083	1.033	27/64	0.444	0.378	0.312
3/4	0.7500	4-1/2	0.768	0.729	1-1/8	1.125	1.088	1.299	1.240	1/2	0.524	0.455	0.375
7/8	0.8750	4	0.895	0.852	1-5/16	1.312	1.269	1.516	1.447	37/64	0.604	0.531	0.375
FASTENERS &													
				Nominal Screw Size				CONominal Screw Length TS					
								Thru 6 in.			Over 6 in.		
roiciaite di Lengii			1/2 and smaller				±0.12			±0.25			
				Over 1/2				±0.25			±0.25		
the parts of a law encourse if many the underhead bearing surface to the outroms and of the service													

‡Length of a lag screw is measured from the underhead bearing surface to the extreme end of the screw.

Description	<b>ERSS</b> A full-bodied bolt with hex head, spaced threads and a gimlet point.						
Applications/ Advantages	Steel, Electro-plated Zinc: For use in wood in non-corrosive environments. Steel, Hot-Dip Galvanized: For use in corrosive environments. Stainless: Has superior corrosion resistance to galvanized steel bolts.						
Material	Steel: AISI 1006 - 1022 or equivalent steel. Stainless: 18-8 stainless.						
Heat Treatment	Stainless: The austenitic alloys develop their strength through work hardening during the fastener manufacturing process, as seen from the hardness properties below. The only heat treatment normally available on austenitic stainless alloys is annealing, which is done at approximately 1900°F to a dead soft condition and is not normally thermally reversible.						
Hardness	Steel: Rockwell B70 - B100. Stainless: 1/4 through 1/2 in. diameter Rockwell B95 - C32.						
Tensile Strength	Steel: 60,000 psi. minimum Stainless: 100,000 - 125,000 psi. (approximate)						
Minimum Thread Length	The minimum length of thread shall be equal to 1/2 the nominal screw length plus 0.50 in., or 5.00 in., whichever is shorter. Screws too short for this formula shall be threaded as close to the head as practicable.						
Plating	See Appendix-A for information on the plating of steel lag bolts.						

Please contact us at: (623) 516-1551 | www.rcfastener.com | sales@rcfastener.com